

# Cutech Alloys Private Limited

## USA- ASTM

Aluminium Bronze													
Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C60800	Rem.		0.1		0.1			5-6.5					
C61000	Rem.		0.02	0.2	0.5			6-8.5		0.1			
C61300	Rem,	0.2-0.5	0.01	0.1	2-3	0.15	0.015	6-7.5	0.2	0.1			
061400	Rem.		0.01	0.2	1.5-3.5		0.015	6-8	1				
C61500	Rem.		0.015			1.8-2.2		7.7-8.3					
C61550	Rem,	0.05	0.05		0.2	1.5-2.5		5.5-6.5					
C61800	Rem.		0.02	0.02	0.5-1.5			8.5-11		0.1			
C61900	Rem.	0.6	0.02	0.8	3-4.5			8.5-10					
C62200	Rem.		0.02	0.02	3-4.2			11-12		0.1			
C62300	Rem.	0.6			2-4	1		8.5-10	0.5	0.25			
C62400	Rem,	0.2			2-4.5			10-11.5	0.3	0.25			
C62500	Rem.				3.5-5.5			12.5- 13.5	2				
C62580	Rem.		0.02	0.02	3-5			12-13		0.04			
C62581	Rem.		0.02	0.02	3-5			13-14		0.04			
C62582	Rem.		0.02	0.2	3-5			14-15		0.04			
C63000	Rem.	0.2		0.3	2-4	4-5.5		9-11	1.5	0.25			
C63010	78 Min	0.2		0.3	2-3.5	4.5-5.5		9.7-10.9	1.5				
C63020	74.5 Min	0.25	0.03	0.3	4-5.5	4.2-6		10-11	1.5				
C63200	Rem.		0.02		3.5-4.3	4-4.8		8.7-9.5	1.2-2	0.1			
C63280	Rem.		0.02		3-5	4-5.5		8.5-9.5	0.6-3.5				
C63380	Rem.		0.02	0.15	2-4	1.5-3		7-8.5	11-14	0.1			
C95200	86 Min				2.5-4			8.5-9.5					
C95210	86 Min	0.1	0.05	0.5	2.5-4	1		8.5-9.5	1	0.25			
C95220	Rem.				2.5-4	2.5		9.5-10.5	0.5				
C95300	86 Min				0.8-1.5			9-11					
C95400	83 Min				3-5	1.5		10-11.5	0.5				
C95410	83 Min				3-5	1.5-2.5			0.5				

# Cutech Alloys Private Limited

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C95420	83.5 Min				2-4.5	0.5		10.5-12	0.5				
C95500	78 Min				3-5	3-5.5		10-11.5	3.5				
C95510	78 Min	0.2		0.3	2-3.5	4.5-5.5		9.7-10.9	1.5				
C95520	74.5 Min	0.25	0.03	0.3	4-5.5	4.2-6		10.5-11.5	1.5	0.15			
C95700	71 Min				2-4	1.5-3		7-8.5	11-14	0.1			
C95710	71 Min	1	0.05	0.5	2-4	1.5-3		7-8.5	11-14	0.15			
C95720	73 Min	0.1	0.03	0.1	1.5-3.5	3-6		6-8	12-15	0.1			
C95800	78 Min		0.03		3.5-4.5	4-5		8.5-9.5	0.8-1.5	0.1			
C95810	79 Min		0.1	0.5	3.5-4.5	4-5		8.5-9.5	0.8-1.5	0.1			
C95820	77.5 Min	0.2	0.02	0.2	4-5	4.5-5.8		9-10	1.5	0.1			
C95900	Rem.				3-5	0.5		12-13.5	1.5				

Tin Bronze													
Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C89320	87-91	5-7	0.09	1	0.2	1	0.3	0.005		0.005	0.35	0.08	4-6
C40820	94 Min	1-2.5	0.02	0.2-2.5		0.1-0.5	0.05						
C50100	Rem.	0.5-0.8	0.05		0.05		0.01-0.05						
C50200	Rem.	1-1.5	0.05		0.1		0.04						
C50500	Rem.	1-1.7	0.05	0.3	0.1		0.03-0.35						
C50510	Rem.	1-1.5		0.1-0.25		0.15-0.4	0.02-0.07						
C50580	Rem.	1-1.7	0.05	0.3	0.05-0.2	0.05-0.2	0.01-0.35						
C50590	Rem.	0.5-1.5	0.02	0.5	0.05-0.4		0.02-0.15						
C50700	Rem.	1.5-2	0.05		0.1		0.3						
050705	Rem.	1.5-2	0.02	0.5	0.1-0.4		0.04-0.15						
050710	Rem.	1.7-2.3				0.1-0.4	0.15						
C50715	Rem.	1.7-2.3	0.02		0.05-0.15		0.025-0.04						
C50725	Rem.	1.5-2.5	0.02	1.5-3	0.05-0.2		0.02-0.06						
C50780	Rem.	1.7-2.3	0.05	0.3	0.05-0.2	0.05-0.2	0.01-0.35						
C50900	Rem.	2.5-3.8	0.05	0.3	0.1		0.03-0.3						
C51000	Rem.	4.2-5.8	0.05	0.3	0.1		0.03-0.35						

# Cutech Alloys Private Limited

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C51080	Rem.	4.8-5.8	0.05	0.3	0.05-0.2	0.05-0.2	0.01-0.35						
C51100	Rem.	3.5-4.9	0.05	0.3	0.1		0.03-0.35						
C51180	Rem.	3.5-4.9	0.05	0.3	0.05-0.2	0.05-0.2	0.01-0.35						
C51190	Rem.	3-6.5	0.02		0.05-0.15		0.025-0.045						
C51800	Rem.	4-6	0.02				0.10-0.35	0.01					
C51900	Rem.	5-7	0.05	0.3	0.1		0.3-0.35						
C51980	Rem.	5.5-7	0.05	0.3	0.05-0.2	0.05-0.2	0.01-0.35						
C52100	Rem.	7-9	0.05	0.2	0.1		0.03-0.35						
C52180	Rem.	7-9	0.05	0.3	0.05-0.2	0.05-0.2	0.01-0.35						
C52400	Rem.	9-11	0.05	0.2	0.1		0.03-0.35						
C52480	Rem.	9-11	0.05	0.3	0.05-0.2	0.05-0.2	0.1-0.35						
C53400	Rem.	3.5-5.8	0.8-1.2	0.3	0.1		0.03-0.35						
C53800	Rem.	13.1-13.9	0.4-0.6	0.1	0.03	0.03			0.06				
C89325	84-88	9-11	0.1	1	0.15	1	0.1	0.005		0.005	0.5	0.08	2.7- 3.7
C89510	86-88	4-6	0.25	4-6	0.2	1	0.05	0.005		0.005	0.25	0.08	0.5-1.5
C89520	85-87	5-6	0.25	4-6	0.2	1	0.05	0.005		0.005	0.25	0.08	1.6-2.2
C89530	84-89	3.5-6	0.2	7-9	0.3	1	0.05	0.01		0.01	0.2		1-2
C89831	87-91	2.7-3.7	0.1	2-4	0.3	1	0.05	0.005		0.005	0.25	0.08	2.7-3.7
C89833	87-91	4-6	0.1	2-4	0.3	1	0.05	0.005		0.005	0.25	0.08	1.7-2.7
C89835	85-89	6-7.5	0.1	2-4	0.2	1	0.1	0.005		0.005	0.35	0.08	1.7-2.7
C89836	87-91	4-7	0.25	2-4	0.35	0.9	0.06	0.005		0.005	0.25	0.08	1.5-35
C89837	84-88	3-4	0.1	6-10	0.3	1	0.05	0.005		0.005	0.25	0.08	0.7-1.2
C89844	83-86	3-5	0.2	7-10	0.3	1	0.05	0.005		0.005	0.25	0.08	2-4
C89940	64-68	3-5	0.01	3-5	0.7-2	20-23	0.1-0.15	0.005		0.15	0.2	0.05	4-5.5
C90300	86-89	7.5-9	0.3	3-5	0.2	1	0.05	0.005		0.005	0.2	0.05	
C90200	91-94	6-8	0.3	0.5	0.2	0.5	0.05	0.005		0.005	0.2	0.05	
C90500	86-89	9-11	0.3	1-3	0.2	1	0.05	0.005		0.005	0.2	0.05	
C90700	88-90	10-12	0.5	0.5	0.15	0.5	0.3	0.005		0.005	0.2	0.05	
C30710	REM.	10-12	0.25	0.05	0.1	0.1	0.05-1.2	0.005		0.005	0.2	0.05	
C90800	85-89	11-13	0.25	0.25	0.15	0.5	0.3	0.005		0.005	0.2	0.05	
C90810	Rem.	11-13	0.25	0.3	0.15	0.5	0.15-0.8	0.005		0.005	0.2	0.005	

# Cutech Alloys Private Limited

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C90900	86-89	12-14	0.25	0.25	0.15	0.5	0.05	0.005		0.005	0.2	0.005	
C91000	84-86	14-16	0.2	1.5	0.1	0.8	0.05	0.005		0.005	0.2	0.005	
C91100	82-85	15-17	0.25	0.25	0.25	0.5	1.00	0.005		0.005	0.2	0.005	
C91300	79-82	18-20	0.25	0.25	0.25	0.5	1.00	0.005		0.005	0.2	0.005	
C91600	86-89	9.7-10.3	0.25	0.25	0.2	1.2-2	0.30	0.005		0.005	0.2	0.005	
C91700	84-87	11.3-12.5	0.25	0.25	0.2	1.2-2	0.30	0.005		0.005	0.2	0.005	
C92200	86-90	5.5-6.5	1-2	3-5	0.25	1.0	0.05	0.005		0.005	0.25	0.05	
C92300	85-89	7.5-9	0.3-1	2.5-5	0.25	1.0	0.05	0.005		0.005	0.25	0.05	
C92310	Rem.	7.5-8.5	0.3-1.5	3.5-4.5		1.0		0.005	0.03	0.005			
C92400	86-89	9-11	1-2.5	1-3	0.25	1.0	0.05	0.005		0.005	0.25	0.05	
C92500	85-88	10-12	1-1.5	0.5	0.3	0.8-1.5	0.30	0.005		0.005	0.25	0.05	
C92600	86-88.5	9.3-10.5	0.8-1.5	1.3-2.5	0.2	0.7	0.03	0.005		0.005	0.25	0.05	
C92610	Rem.	9.5-10.5	0.3-1.5	1.7-2.8	0.15	1.0		0.005	0.03	0.005			
C92700	86-89	9-11	1-2.5	0.7	0.2	1.0	0.25	0.005		0.005	0.25	0.05	
C92710	Rem.	9-11	4 - 6	1	0.2	2.0	0.10	0.005		0.005	0.25	0.05	
C92800	78-82	15-17	4 - 6	0.8	0.2	0.8	0.05	0.005		0.005	0.25	0.05	
C92810	78-82	12-14	4 - 6	0.5	0.5	0.8-1.2	0.05	0.005		0.005	0.25	0.05	
C92900	82-86	9-11	2-3.2	0.25	0.2	2.8- 4	0.500	0.005		0.005	0.25	0.05	
C93100	Rem.	6.5-8.5	2- 5	2	0.25	1.0	0.300	0.005		0.005	0.25	0.05	
C93200	81-85	6.3-7.5	6 - 8	1-4	0.2	1.000	0.15	0.005		0.005	0.35	0.08	

Gun Metal													
Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C83300	92-94	1-2	1-2	2-6									
C83450	87-89	2.2-3	1.5-2.5	5.5-7.5	0.25	0.8 - 1.5	0.03	0.005		0.005	0.25	0.08	
C83500	86-88	5.5-6.5	3.5-5.5	1-2.5	0.25	0.5- 1	0.03	0.005		0.005	0.25	0.08	
C83600	84-86	4.3-6	4-5.7	4.3-6	0.25	1.000	0.05	0.005		0.005	0.25	0.08	
C83800	82-83.5	3.5-4.2	5.8-6.8	5.5-8	0.25	1.000	0.03	0.005		0.005	0.25	0.08	
C83810	Rem.	2-3.5	4-6	7.5-9.5	0.5	2.000		0.005		0.1			
C84200	78-82	4-6	2-3	10-16	0.4	0.800	0.05	0.005		0.005	0.25	0.08	

# Cutech Alloys Private Limited

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C84400	79-82	2.5-3.5	6-8	7-10	0.4	0.800	0.020	0.005		0.005	0.25	0.08	
C84410	Rem.	3-4.5	7-9	7-11		1.000		0.010		0.20			0.05
C84500	77-79	2-4	6-7.5	10-14	0.4	1.000	0.02	0.005		0.005	0.250	0.08	
C84800	75-76.7	2-3	5.5-7	13-17	0.4	1.000	0.02	0.005		0.005	0.250	0.080	
C92210	86-89	4.5-5.5	1.7-2.5	3- 4.5	0.250	0.7 -1	0.03	0.005		0.005	0.2	0.05	
C92220	86-88	5 -6	1.5-2.5	3-5.5	0.25	0.5 - 1	0.05						
C54400	Rem.	3.5-4.5	3.5-4.5	1.5-4.5	0.1		0.01-0.5						

Silicon Brass													
Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C23030	83.5-85.5		0.05	Rem.	0.05					0.2-0.4			
C69050	70-75			Rem.		0.5-1.5		3-4		0.1-0.6			
C69100	81-84	0.1	0.05	Rem.	0.25	0.8-1.4		0.7-1.2	0.1	0.8-1.3			
C69300	73-77	0.2	0.1	Rem.	0.1	0.1	0.04-0.15		0.1	2.7-3.4			
C69400	80-83		0.3	Rem.	0.2					3.5-4.5			
C69430	80-83		0.3	Rem.	0.2					3.5-4.5			
C69700	75-80		0.5-1.5	Rem.	0.2				0.4	2.5-3.5			
C69710	75-80		0.5-1.5	Rem.	0.2				0.4	2.5-3.5			
C69750	78-83	0.05	0.8-1.3	Rem.	0.05	0.01	0.02		0.05	1.9-2.22			
C87400	79 Min		1	12-16				0.8		2.5-4			
C87500	79 Min		0.5	12-16				0.5		3-5			
C87600	88 Min		0.5	4-7	0.2				0.25	3.5-5.5			
C87610	90 Min		0.2	3-5	0.2				0.25	3-5			
C87800	80 Min	0.25	0.15	12-16	0.15	0.2	0.01	0.15	0.15	3.8-4.2	0.05	0.05	
C87850	74-78	0.3	0.1	Rem.	0.1	0.2	0.05-0.2		0.1	2.7-3.4	0.1		

Recycled To PERFECTION





# Cutech Alloys Private Limited

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C37710	56.5-60		1-3	Rem.	0.3								
C38000	55-60	0.3	1.5-2.5	Rem.	0.35			0.5					
C38500	55-59		2.5-3.5	Rem.	0.35								
C40400	Rem.	0.35-0.7		2-3									
C40500	94-96	0.7-1.3	0.05	Rem.	0.05								
C40810	94.5-96.5	1.8-2.2	0.05	Rem.	0.08-0.12	0.11-0.2	0.028-0.4						
C40850	94.5-96.5	2.6-4	0.05	Rem.	0.05-0.2	0.05-0.2	0.01-0.2						
C40860	94-96	1.7-2.3	0.05	Rem.	0.01-0.05	0.05-0.2	0.02-0.04						
C41000	91-93	2-2.8	0.05	Rem.	0.05								
C41100	89-92	0.3-0.7	0.1	Rem.	0.05								
C41120	89-92	0.3-0.7	0.05	Rem.	0.05-0.2	0.05-0.2	0.01-0.35						
C41300	89-93	0.7-1.3	0.1	Rem.	0.05								
C41500	89-93	1.5-2.2	0.1	Rem.	0.05								
C42000	88-91	1.5-2		Rem.			0.25						
C42200	86-89	0.8-1.4	0.05	Rem.	0.05		0.35						
C42220	88-91	0.7-1.4	0.05	Rem.	0.05-0.2	0.05-0.2	0.02-0.05						
C42500	87-90	1.5-3	0.05	Rem.	0.05		0.35						
C42520	88-91	1.5-3	0.05	Rem.	0.05-0.2	0.05-0.2	0.01-0.2						
C42600	87-90	2.5-4	0.05	Rem.	0.05-0.2	0.05-0.2	0.01-0.2						
C43000	84-87	1.7-2.7	0.1	Rem.	0.05								
C43400	84-87	0.4-1	0.05	Rem.	0.05								
043500	79-83	0.6-1.2	0.1	Rem.	0.05								
C43600	80-83	0.2-0.5	0.05	Rem.	0.05								
C44250	73-76	0.5-1.5	0.07	Rem.	0.2	0.2	0.1						
C44300	70-73	0.8-1.2	0.07	Rem.	0.06								
C44400	70-73	0.8-1.2	0.07	Rem.	0.06						0.02-0.1		
C44500	70-73	0.8-1.2	0.07	Rem.	0.06		0.02-0.1						
C46200	62-65	0.5-1	0.2	Rem.	0.1								
C46400	59-62	0.5-1	0.2	Rem.	0.1								
C46500	59-62	0.5-1	0.2	Rem.	0.1								
C47000	57-61	0.25-1	0.05	Rem.				0.01					



# Cutech Alloys Private Limited

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C47940	63-66	1.2-2	1-2	Rem.	0.1-1	0.1-0.5							
C48200	59-62	0.5-1	0.4-1	Rem.	0.1								
C48500	59-62	0.5-1	1.3 - 2.2	Rem.	0.1								
C48600	59-62	0.3-1.5	1- 2.5	Rem.									
C66200	86.6-91	0.2-0.7	0.05	Rem.	0.05	0.30-1	0.05-0.2						
C66300	84.5-87.5	1.5-3	0.05	Rem.	1.4-2.4		0.35						
C66400	Rem.	0.05	0.015	11-12	1.3-1.7								
C66410	Rem.	0.05	0.015	11-12	1.8-2.3								
C66420	Rem.			12.7-17	0.5-1.5								
C66430	Rem.	0.6-0.9	0.05	13-15	0.6-0.9		0.1						
C67500	57-60	0.5-1.5	0.2	Rem.	0.8-2			0.25	0.05-0.5				
C67600	57-60	0.5-1.5	0.5-1	Rem.	0.4-1.3				0.05-0.5				
C68000	56-60	0.75-1.1	0.05	Rem.	0.25-1.25	0.2-0.8		0.01	0.01-0.5	0.04-0.15			
C68100	56-60	0.75-1.1	0.05	Rem.	0.25-1.2			0.01	0.01-0.5	0.04-0.15			
C68700	76-79		0.07	Rem.	0.06			1.8-2.5					
C68800	Rem.		0.05	21.3-24.1	0.2			3-3.8					
C83400	88-92	0.2	0.5	8-12	0.25	1	0.03	0.005		0.005	0.25	0.08	
C85200	70-74	0.7-2	1.5-3.58	20-27	0.6	1	0.02	0.005		0.05	0.2	0.05	
C85400	65-70	0.5-1.5	1.5-3.8	24-32	0.7	1		0.35		0.05			
C85500	59-63	0.2	0.2	Rem.	0.2	0.2			0.2				
C85700	58-64	0.5-1.5	0.8-1.5	32-40	0.7	1		0.8		0.05			
C85710	58-63	1	1-2.5	32-39	0.8	1		0.2-0.8	0.5	0.05			
C85800	57Min	1.5	1.5	31-41	0.5	0.5	0.01	0.55	0.25	0.25	0.05	0.05	
C89540	58-64	1.2	0.1	32-38	0.5	1		0.1-0.6					0.6-1.2
C89550	58-64	1.2	0.1	32-38	0.5	1	0.01	0.1-0.6		0.25	0.05	0.05	0.6-1.2

RECYCLED TO PERFECTION

# Cutech Alloys Private Limited

## High Tensile Brass

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C66700	68.5-71.5		0.07	Rem.	0.1				0.8-1.5				
C66800	60-63	0.3	0.5	Rem.	0.35	0.25		0.25	2-3.5	0.5-1.5			
C66900	62.5-64.5		0.05	Rem.	0.25				11.5-12.5				
C66950	Rem.		0.01	14-15	0.5			1-1.5	14-15				
C67000	63-68	0.5	0.2	Rem.	2-4			3-6	2.5-5				
C67300	58-63	0.3	0.4-3	Rem.	0.5	0.25		0.25	2-3.5	0.5-1.5			
C67400	57-60	0.3	0.5	Rem.	0.35	0.25		0.5-2	2-3.5	0.5-1.5			
C67420	57-58.5	0.35	0.25-0.8	Rem.	0.15-0.55	0.25		1-2	1.5-2.5	0.25-0.7			
C86100	66-68	0.2	0.2	Rem.	2-4			4.5-5.5	2.5-5				
C86200	60-66	0.2	0.2	22-28	2-4	1		3-4.9	2.5-5				
C86300	60-66	0.2	0.2	22-28	2-4	1		5-7.5	2.5-5				
C86400	56-62	0.5-1.5	0.5-1.5	34-42	0.4-2	1		0.5-1.5	0.1-1.5				
C86500	55-60	1	0.4	36-42	0.4-2	1		0.5-1.5	0.1-1.5				
C86550	57 Min	1	0.5	Rem.	0.7-2	1		0.5-2.5	0.1-3	0.1			
C86700	55-60	1.5	0.5-1.5	30-38	1-3	1		1-3	0.1-3.5				
C86800	53.5-57	1	0.2	Rem.	1-2.5	2.5-4		2	2.5-4				
C99700	54 Min	1	0.2	19-25	1	4-6		0.5-3	11-15				
C99750	55-61		0.5-2.5	17-23	1	5		0.25-3	17-23				

## Silicon Bronze

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C63400	Rem.	0.2	0.05	0.5	0.15	0.15		2.6-3.2		0.25-0.45			
C63600	Rem.	0.2	0.05	0.5	0.15	0.15		3-4		0.7-1.3			
C63800	Rem.		0.05	0.8	0.2	0.2		2.5-3.1	0.1	1.5-2.1			
C64200	Rem.	0.2	0.05	0.5	0.3	0.25		6.3-7.6	0.1	1.5-2.2			
C64210	Rem.	0.2	0.05	0.5	0.3	0.25		6.3-7	0.1	1.5-2			
C87300	94 Min		0.2	0.25	0.2				0.8-1.5	3.5-4.5			
C95600	88 Min					0.25		6-8		1.8-3.2			

# Cutech Alloys Private Limited

Cu Ni Bronze														
Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Sb	Al	Mn	Si	Sb	S	Bi
C94700	85-90	4.5-6	0.1	1-2.5	0.25	4.5-6	0.05	0.005	0.2	0.005	0.15	0.05		
C94800	84-89	4.5-6	0.3-1	1-2.5	0.3	4.5-6	0.05	0.005	0.2	0.005	0.15	0.05		
C94900	79-81	4-6	4-6	4-6	0.25	4-6	0.05	0.005	0.1	0.005	0.25	0.08		
C96200	Rem.		0.01		1-1.8	9-11	0.02		1.5	0.5				
C96300	Rem.		0.01		0.5-1.5	18-22	0.02		0.25-1.5	0.5				
C96400	Rem.		0.01		0.25-1.5	28-32	0.02		1.5	0.5				
C96600	Rem.		0.01		0.8-1.1	29-33			1	0.15				
C96700	Rem.		0.01		0.4-1	29-33			0.4-1	0.15				
C96800	Rem.	7.5-8.5	0.005	1	0.5	9.5-10.5			0.05-0.3	0.05				
C96900	Rem.	7.5-8.5	0.02	0.5	0.5	14.5-15.5			0.05-0.3					
C96950			0.02		0.05	11-15.5			0.05-0.4	0.3				
C96970	Rem.	5.5-6.5	0.02	0.5	0.5	8.5-9.5			0.3					
C97300	53-58	1.5-3	8-11	17-25	1	11-14	0.05	0.005	0.5	0.05	0.35	0.08		
C97600	63-66	3.5-4.5	3.5-5	3-9	1	19.5-21	0.05	0.005	1	0.05	0.25	0.08		
C97800	64-67	4.5-5.5	1-2	1-4	1	24-26	0.05	0.005	1	0.05	0.2	0.08		
C99400	Rem.		0.25	5	5.5	5.5		2		2				
C99500	Rem.		0.25	2	5.5	5.5		2		2				

Cutech  
 RECYCLED TO PERFECTION